

REM-AK OC

Modified alkyd monolayer

Product properties

Contains anticorrosive pigments
 Excellent adhesion on blasted steel
 Fast drying

Recommended uses

It is applied as a primer or monolayer.
 For protection of steel constructions, apparatus and machine structures, pipes.

Product data

Colour	according to RAL card or sample
Gloss	Semi-Matt
Volume solids with	45 %
Spec. Gravity	1,2 g/cm ³
VOC	483 g/l According directive 2010/75/EU
Theoretical coverage	80 µm DFT 5,4 m ² /l 4,5 m ² /kg
Typical thickness	60 - 120 µm

Curing table for dry film thickness up to 40 µm	
Substrate temperature	20 °C
Dry to touch	30 min
Dry to handle	50 min
Overcoating, minimum	5 hrs
Overcoating, maximum	According to Kansai Helios technical guidelines

Thinner	VERDÜNNUNG 87052
Thinner	VERDÜNNUNG 500

Recommended substrate preparation

All surfaces to be coated shall be clean, dry and free from any contamination. Before application of the paint, all steel surfaces shall be assessed and treated in accordance with ISO 8501 and ISO 8504. The coating must be applied to the specified thickness, as soon as possible after the surface is properly prepared. Weld spatter, sharp weld seams and sharp edges shall be removed.

Steel	Blast cleaning to Sa 2 ½ according to ISO 8501-1:2007.
--------------	--





Preparing of mixture

Mixing	Stir container with a high-speed agitator for at least 90 seconds with a toothed dispersion blade before use.
---------------	---

Application

REM-AK OC

Modified alkyd monolayer

	Airless	Thinning by weight up to 3 %	Nozzle 0,011 - 0,021 "	Pressure at least 180 bar
	Air Spray	Thinning by weight up to 3 %	Nozzle 1,5 mm	Pressure at least 2 bar
	Brush	For small areas and stripe coating Thinning: by weight up to 3 %		
	Roller	For small areas Thinning: by weight up to 3 %		
Repair		Prior to overcoating, the existing coating shall be dry, free from any loose paint, grease, oil and any other contaminants.		

Apply only on a clean and dry surface with a temperature at least 3 °C above the dew point to avoid condensation.
 Substrate temperature during application and curing shall be above 5 °C.
 Relative humidity during application and curing shall not exceed 80 %.
 Do not thin more than allowed by local environmental legislation.
 Adequate ventilation shall be maintained during application and curing.
 Too much solvent results in a reduced sag resistance and slower cure.

Additional information

Following further information can be found on www.kansai-helios.eu

Kansai Helios technical guidelines

Remarks

The provided information should be considered only as a guidance. Drying and curing times are determined under controlled temperatures and relative humidity below 80% and at average of the DFT range for the product. The actual drying times before overcoating may be different, depending on film thickness, ventilation, humidity, underlying paint system etc. Excessive application will extend both the minimum overcoating periods and handling times and may affect long term overcoating properties. When the maximum recoating time is exceeded, it might be necessary to roughen the surface before overcoating. When in doubt, consult KANSAI HELIOS.

Cleaning	Clean all equipment with the prescribed cleaner immediately after use.
-----------------	--

REM-AK OC

Modified alkyd monolayer

Recommended coating system

System compatibility

Topcoat: REM-AK DS GLIMMER EXPRESS

Safety precautions

This product is intended for use only by professionals and with reference to the corresponding Safety data sheet. All work involving the application, use and handling of this product shall be done in accordance with relevant national HSE regulations.

Storage and shelf life

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life:	REM-AK OC	12 Month from manufacture in unopened can.
-------------	-----------	--

Subjected to re-inspection thereafter.

Disclaimer

The provided information is based on our experience and on current knowledge, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the user to test, whether the product is suitable for the intended purpose, before using it. Any change in the processing procedure, the environmental conditions, or the failure to comply with instructions may unfavorably influence the result.

We accept no liability for the performance of the product or for any loss or damage arising out of the use of the product unless we expressly agreed otherwise in writing. We disclaim any, express or implied, warranties of merchantability, satisfactory quality or fitness for a particular purpose, functionality or non-infringement, except to the extent such warranties are legally incapable of exclusion. No representation or other affirmation of fact, including but not limited to statements regarding capacity, suitability for use or performance of the product, whether made by our employee or otherwise, shall be deemed to be a warranty for any purpose or give rise to any liability. No oral or written information or advice given shall create a warranty or in any way increase the scope of any warranty.

You should review this document carefully whereby the document itself is subject to modification from time to time. The user is responsible to check that this document is current version before using the product. This document is available on our website at www.kansai-helios.at. If there are any discrepancies between this document and the version on the website, then the website version will take precedence.