

# REMOPLAST STWB

## Two component high solid epoxy coating

### Product properties

High build product  
 Low VOC product  
 Excellent adhesion on blasted steel  
 Very good resistance to freshwater

### Product data

<b>Colour</b>	limited selection, grey
<b>Volume solids with HÄRTER STWB</b>	80 %
<b>Spec. Gravity</b>	1,62 g/cm <sup>3</sup>
<b>VOC with HÄRTER STWB</b>	166 g/l According directive 2010/75/EU
<b>Theoretical coverage</b>	200 µm DFT  4,2 m <sup>2</sup> /l 2,5 m <sup>2</sup> /kg
<b>Typical thickness with HÄRTER STWB</b>	200 µm

<b>Curing table for dry film thickness up to 250 µm</b>	<b>with HÄRTER STWB</b>
---	-------------------------

<b>Mixing ratio with HÄRTER STWB</b>	3,9 : 1 by volume 7 : 1 by weight
<b>Working pot life</b>	20 °C 1,5 hrs

<b>Thinner</b>	<b>VERDUENNUNG 400 TL/TP 687.150</b>
----------------	--------------------------------------

### Recommended substrate preparation

All surfaces to be coated shall be clean, dry and free from any contamination. Before application of the paint, all steel surfaces shall be assessed and treated in accordance with ISO 8501 and ISO 8504. The coating must be applied to the specified thickness, as soon as possible after the surface is properly prepared. Weld spatter, sharp weld seams and sharp edges shall be removed.

<b>Steel</b>	Blast cleaning to Sa 2 ½ according to ISO 8501-1:2007. Roughness profile grade medium (G), according to ISO 8503-1:2012. The coating shall be applied immediately after the blasting and the quality of the surface was approved.
<b>Coated surfaces</b>	Clean, dry approved primer. The surface of the previous coating shall be sufficiently roughened if necessary.




### Preparing of mixture

<b>Mixing</b>	Agitate part A with power agitator. Add part B (hardener) in the specified amount according to the mixing ratio. Agitate thoroughly with power agitator until liquids are homogeneous mixed. Thinner shall be added after mixing or the two components.
---------------	---

### Application

# REMOPLAST STWB

## Two component high solid epoxy coating

	<b>Thinning</b>	<b>Nozzle</b>	<b>Pressure</b>
 <b>Airless</b>	by weight up to 3 %	0,017 - 0,021 "	at least 180 bar
 <b>Brush</b>	For small areas and stripe coating Thinning: by weight up to 3 %		
 <b>Roller</b>	For small areas Thinning: by weight up to 3 %		
<b>Repair</b>	Prior to overcoating, the existing coating shall be dry, free from any loose paint, grease, oil and any other contaminants.		

Apply only on a clean and dry surface with a temperature at least 3 °C above the dew point to avoid condensation.  
 Substrate temperature during application and curing shall be above 8 °C.  
 Relative humidity during application and curing shall not exceed 80 %.

### Additional information

Following further information can be found on [www.kansai-helios.eu](http://www.kansai-helios.eu)

### Kansai Helios technical guidelines

### Remarks

The provided information should be considered only as a guidance. Drying and curing times are determined under controlled temperatures and relative humidity below 80% and at average of the DFT range for the product. The actual drying times before overcoating may be different, depending on film thickness, ventilation, humidity, underlying paint system etc. Excessive application will extend both the minimum overcoating periods and handling times and may affect long term overcoating properties. When the maximum recoating time is exceeded, it might be necessary to roughen the surface before overcoating. When in doubt, consult KANSAI HELIOS.

<b>UV and colour stability</b>	Like all epoxy coatings, this product tends to chalk and discolor on outside exposure (UV light).
<b>Suitability and use</b>	This material can be used under atmospheric and submerged conditions, depending on the system. Maximum temperature resistance 80°C under dry conditions. Maximum temperature resistance 40°C when exposed to water.
<b>Cleaning</b>	Do not allow the paint to stay in hoses, gun or spray equipment. Clean all equipment with the prescribed cleaner immediately after use. Do not exceed pot life limitation!

# REMOPLAST STWB

## Two component high solid epoxy coating

### Recommended coating system

---

#### System compatibility

**Primer:** REMOPLAST EP-ZINK  
REMOPLAST STWB PRIMER

### Safety precautions

---

This product is intended for use only by professionals and with reference to the corresponding Safety data sheet. All work involving the application, use and handling of this product shall be done in accordance with relevant national HSE regulations.

### Storage and shelf life

---

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life:	REMOPLAST STWB	12 Month from manufacture in unopened can.
	HÄRTER STWB	12 Month from manufacture in unopened can.

Subjected to re-inspection thereafter.

### Disclaimer

---

The provided information is based on our experience and on current knowledge, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the user to test, whether the product is suitable for the intended purpose, before using it. Any change in the processing procedure, the environmental conditions, or the failure to comply with instructions may unfavorably influence the result.

We accept no liability for the performance of the product or for any loss or damage arising out of the use of the product unless we expressly agreed otherwise in writing. We disclaim any, express or implied, warranties of merchantability, satisfactory quality or fitness for a particular purpose, functionality or non-infringement, except to the extent such warranties are legally incapable of exclusion. No representation or other affirmation of fact, including but not limited to statements regarding capacity, suitability for use or performance of the product, whether made by our employee or otherwise, shall be deemed to be a warranty for any purpose or give rise to any liability. No oral or written information or advice given shall create a warranty or in any way increase the scope of any warranty.

You should review this document carefully whereby the document itself is subject to modification from time to time. The user is responsible to check that this document is current version before using the product. This document is available on our website at [www.kansai-helios.at](http://www.kansai-helios.at). If there are any discrepancies between this document and the version on the website, then the website version will take precedence.