

REMOPLAST UVC GLIMMER

Two component acrylic polyurethane topcoat

Product properties

Fast drying
 Good mechanical strength and corrosion protection
 Based on acryl resin with functional OH groups.
 It is applied in combination with aliphatic isocyanate hardener.

Recommended uses

Used in environments with high corrosivity, providing long lasting protection.
 Used in the protective systems of different steel construction, railway vehicles, construction and agricultural machinery.

Product data

Colour	according to RAL card or sample
Gloss	Semi – gloss
Volume solids with PU-HAERTER 400 UVC	53 % ± 2
Spec. Gravity	1,3 g/cm ³
VOC with PU-HAERTER 400 UVC	317 g/l According directive 2010/75/EU
Theoretical coverage	80 µm DFT 8 m ² /l 5 m ² /kg
Typical thickness with PU-HAERTER 400 UVC	80 µm

Curing table for dry film thickness up to 80 µm	with PU-HAERTER 400 UVC		
Substrate temperature	23 °C	15 °C	5 °C
Dry to touch	20 min	30 min	2 hrs
Dry to handle	6 hrs	8 hrs	48 hrs
Overcoating, minimum	6 hrs	8 hrs	48 hrs
Overcoating, maximum	According to Kansai Helios technical guidelines		

Mixing ratio with PU-HAERTER 400 UVC	8,0 : 1 by volume 10 : 1 by weight	
Working pot life	20 °C 3 hrs	30 °C 90 min

Thinner	VERDUENNUNG 200 TL/TP 687.151
----------------	--------------------------------------

Recommended substrate preparation

All surfaces to be coated shall be clean, dry and free from any contamination. Before application of the paint, all steel surfaces shall be assessed and treated in accordance with ISO 8501 and ISO 8504. The coating must be applied to the specified thickness, as soon as possible after the surface is properly prepared. Weld spatter, sharp weld seams and sharp edges shall be removed.

Coated surfaces	Clean, dry approved primer. Clean, dry and undamaged compatible coating. The surface of the previous coating shall be sufficiently roughened if necessary.
Substrate temperature and application conditions	Substrate temperature during application and curing shall be at least 3°C (5°F) above dew point.





REMOPLAST UVC GLIMMER

Two component acrylic polyurethane topcoat

Preparing of mixture

Mixing	Agitate part A with power agitator. Add part B (hardener) in the specified amount according to the mixing ratio. Agitate thoroughly with power agitator until liquids are homogeneous mixed. Thinner shall be added after mixing or the two components.
---------------	---

Application

	Thinning	Nozzle	Pressure
 Airless	by weight up to 5 %	0,013 - 0,021 "	at least 180 bar
 Air Spray	by weight up to 8 %	1,5 mm	4 bar
 Brush	For small areas and stripe coating Thinning: by weight up to 5 %		
 Roller	For small areas Thinning: by weight up to 5 %		
Repair	Prior to overcoating, the existing coating shall be dry, free from any loose paint, grease, oil and any other contaminants.		

Apply only on a clean and dry surface with a temperature at least 3 °C above the dew point to avoid condensation.
 Substrate temperature during application and curing shall be above 5 °C.
 Relative humidity during application and curing shall not exceed 80 %.
 Thinner shall be added after mixing of the components.
 Do not thin more than allowed by local environmental legislation.
 Too much solvent results in a reduced sag resistance and slower cure.
 Adequate ventilation shall be maintained during application and curing.

Additional information

Following further information can be found on www.kansai-helios.eu

Kansai Helios technical guidelines

REMOPLAST UVC GLIMMER

Two component acrylic polyurethane topcoat

Remarks

The provided information should be considered only as a guidance. Drying and curing times are determined under controlled temperatures and relative humidity below 80% and at average of the DFT range for the product. The actual drying times before overcoating may be different, depending on film thickness, ventilation, humidity, underlying paint system etc. Excessive application will extend both the minimum overcoating periods and handling times and may affect long term overcoating properties. When the maximum recoating time is exceeded, it might be necessary to roughen the surface before overcoating. When in doubt, consult KANSAI HELIOS.

Suitability and use	Temperature resistance: short-term 150°C, permanent max. 120°C
Approvals and certificates	Approved according RVS 15.05.11.
Cleaning	Do not allow the paint to stay in hoses, gun or spray equipment. Clean all equipment with the prescribed cleaner immediately after use. Do not exceed pot life limitation!

Recommended coating system

System compatibility

Primer: REMOPLAST PRIMER
 REM 61 PRIMER
 REMOPLAST KUNSTSTOFFGRUND
 REMOPLAST MSR ULTRAPRIMER

Intermediate Coat: REMOPLAST DS GLIMMER
 REMOPLAST MSR UTRA-IC

Safety precautions

This product is intended for use only by professionals and with reference to the corresponding Safety data sheet. All work involving the application, use and handling of this product shall be done in accordance with relevant national HSE regulations.

Storage and shelf life

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life:	REMOPLAST UVC GLIMMER	24 Month from manufacture in unopened can.
	PU-HAERTER 400 UVC	24 Month from manufacture in unopened can.

Subjected to re-inspection thereafter.

Warning, PU hardeners react with moisture, thus don't leave cans open. Don't store partially used cans of hardener for prolonged time.

REMOPLAST UVC GLIMMER

Two component acrylic polyurethane topcoat

Disclaimer

The provided information is based on our experience and on current knowledge, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the user to test, whether the product is suitable for the intended purpose, before using it. Any change in the processing procedure, the environmental conditions, or the failure to comply with instructions may unfavorably influence the result.

We accept no liability for the performance of the product or for any loss or damage arising out of the use of the product unless we expressly agreed otherwise in writing. We disclaim any, express or implied, warranties of merchantability, satisfactory quality or fitness for a particular purpose, functionality or non-infringement, except to the extent such warranties are legally incapable of exclusion. No representation or other affirmation of fact, including but not limited to statements regarding capacity, suitability for use or performance of the product, whether made by our employee or otherwise, shall be deemed to be a warranty for any purpose or give rise to any liability. No oral or written information or advice given shall create a warranty or in any way increase the scope of any warranty.

You should review this document carefully whereby the document itself is subject to modification from time to time. The user is responsible to check that this document is current version before using the product. This document is available on our website at www.kansai-helios.at. If there are any discrepancies between this document and the version on the website, then the website version will take precedence.