

REMOROL DKX

Product properties

High build film coating material based on modified acrylic resin with safe adherence on fresh and weathered hot-dip galvanization.
 High build product
 Excellent adhesion on hot dip galvanized steel
 For high build layer application on hot-dip galvanizing

Recommended uses

For the protection of power lines,

Product data

Colour	according to RAL card or sample
Gloss	Semi-Matt
Volume solids with	46 % ± 2
Spec. Gravity	1,3 g/cm ³
Theoretical coverage	80 µm DFT 5,7 m ² /l 4,4 m ² /kg
Typical thickness	80 µm

Curing table for dry film thickness up to 80 µm	
Substrate temperature	20 °C
Dry to handle	10 hrs
Overcoating, minimum	24 hrs
Overcoating, maximum	According to Kansai Helios technical guidelines

Thinner	VERDUENNUNG 100 KUNSTHARZ-VERDÜNNUNG
----------------	---

Recommended substrate preparation

All surfaces to be coated shall be clean, dry and free from any contamination. Before application of the paint, all steel surfaces shall be assessed and treated in accordance with ISO 8501 and ISO 8504. The coating must be applied to the specified thickness, as soon as possible after the surface is properly prepared. Weld spatter, sharp weld seams and sharp edges shall be removed.


Hot-dip galvanised steel	The surface must be dry and free from any contamination. Contamination (e.g. zincsalts) has to be removed. New galvanizations must be free of grease and other separating layers.
---------------------------------	---

Preparing of mixture

Mixing	Stir container with a high-speed agitator for at least 90 seconds with a toothed dispersion blade before use.
---------------	---

REMOROL DKX

Application

	<p>Brush</p>	<p>Thinning: by weight up to 3 %</p>
---	---------------------	--------------------------------------

Apply only on a clean and dry surface with a temperature at least 3 °C above the dew point to avoid condensation. Substrate temperature during application and curing shall be above 7 °C. Relative humidity during application and curing shall not exceed 80 %.

Additional information

Following further information can be found on www.kansai-helios.eu

Kansai Helios technical guidelines

Remarks

The provided information should be considered only as a guidance. Drying and curing times are determined under controlled temperatures and relative humidity below 80% and at average of the DFT range for the product. The actual drying times before overcoating may be different, depending on film thickness, ventilation, humidity, underlying paint system etc. Excessive application will extend both the minimum overcoating periods and handling times and may affect long term overcoating properties. When the maximum recoating time is exceeded, it might be necessary to roughen the surface before overcoating. When in doubt, consult KANSAI HELIOS.

<p>Cleaning</p>	<p>Do not allow the paint to stay in hoses, gun or spray equipment. Clean all equipment with the prescribed cleaner immediately after use.</p>
------------------------	--

Safety precautions

This product is intended for use only by professionals and with reference to the corresponding Safety data sheet. All work involving the application, use and handling of this product shall be done in accordance with relevant national HSE regulations.

Storage and shelf life

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

<p>Shelf life:</p>	<p>REMOROL DKX</p>	<p>12 Month from manufacture in unopened can.</p>
--------------------	--------------------	---

Subjected to re-inspection thereafter.

REMOROL DKX

Disclaimer

The provided information is based on our experience and on current knowledge, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the user to test, whether the product is suitable for the intended purpose, before using it. Any change in the processing procedure, the environmental conditions, or the failure to comply with instructions may unfavorably influence the result.

We accept no liability for the performance of the product or for any loss or damage arising out of the use of the product unless we expressly agreed otherwise in writing. We disclaim any, express or implied, warranties of merchantability, satisfactory quality or fitness for a particular purpose, functionality or non-infringement, except to the extent such warranties are legally incapable of exclusion. No representation or other affirmation of fact, including but not limited to statements regarding capacity, suitability for use or performance of the product, whether made by our employee or otherwise, shall be deemed to be a warranty for any purpose or give rise to any liability. No oral or written information or advice given shall create a warranty or in any way increase the scope of any warranty.

You should review this document carefully whereby the document itself is subject to modification from time to time. The user is responsible to check that this document is current version before using the product. This document is available on our website at www.kansai-helios.at. If there are any discrepancies between this document and the version on the website, then the website version will take precedence.